

TEKNİK BİLGİ FORMU / TECHNICAL DATA SHEET**ALÜMİNYUM HİDROKSİT / ALUMINUM HYDROXIDE - Al(OH)₃****Kimyasal İçerik / Chemical Composition [%]**

	Nemli / Wet	Kuru / Dry
Kızdırma Kaybı / Loss on Ignition (1000 °C)	~34.6	~34.6
Al ₂ O ₃	>65.0	>65.0
SiO ₂	<0.015	<0.015
Fe ₂ O ₃	<0.015	<0.015
Na ₂ O	<0.15	<0.15
CaO	<0.030	<0.030

Fiziksel Özellik / Physical Properties

Nem / Moisture [105 °C, 2h]	4-6	0.1-0.3
Beyazlık / Whiteness, Ry 457 nm	>83	>83

Tane Boyut Dağılımı / Particle Size Distribution

d 50 [µm]	90-110	85-110
< 45 µm[%]	<10	<12

Paketleme / Packaging	1.0 MT, 1.1 MT, 1.2 MT (PE-PP Bigbags) Dökme/Bulk	
-----------------------	---	--

Yukarıda verilen değerler ürün tolerans aralıklarına kaynak niteliğindedir. Gerçek değerler analiz sertifikasında verilmektedir.
All data listed above are reference to the product tolerances. The actual values are stated in the Certificate of Analysis.

Kimyasal Tescil Numaraları / Chemical Registration Numbers**CAS No: 21645-51-2 / Reach No : 01-2119529246-39****G.T.İ.P. / H.S.CODE****28183000000****K - Q**
TSE-ISO-EN
9000**C - E**
TSE-ISO-EN
14000**TS-ISO-45001****M - C**
TSE - ISO
10002**TSE**
TSE-ISO-EN
50001

ETİ ALÜMİNYUM A. Ş.

Bir CENGİZ HOLDİNG kuruluşudur.

Merkez Ofis: Altunizade Kısıklı Cd. No: 37 34662 Üsküdar/İSTANBUL

Tel: +90 216 554 53 00 (Pbx) Faks: +90 216 474 11 22

E-mail: mining@cengiz.com.tr

Fabrika: Atatürk Caddesi 42370 Seydişehir/KONYA

Tel: +90 332 582 30 30 (Pbx) Faks: +90 332 582 39 27

E-mail: pazarlama@etaluminyum.comwww.etaluminyum.com

Rev :12.06.19